

Entec Hylox® 9030 PBT, 30% Glass Reinforced

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

Entec's proprietary products include a full range of compounds in the Nylon 6/6, Nylon 6, ABS, PBT, Polycarbonate, PC/ABS, PC/ASA, PC/PBT, and PPO/PPE resin families. Information provided by Entec.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Entec-Hylox-9030-PBT-30-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.52 g/cc	0.0549 lb/in ³	ASTM D792
Water Absorption	0.060 %	0.060 %	24 hrs; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	0.125 in; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	91	91	ASTM D785
Tensile Strength at Break	132 MPa	19200 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	197 MPa	28500 psi	ASTM D790
Flexural Modulus	8.83 GPa	1280 ksi	ASTM D790
Izod Impact, Notched	0.908 J/cm	1.70 ft-lb/in	73°F; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	30.6 µm/m-°C @Temperature 20.0 °C	17.0 µin/in-°F @Temperature 68.0 °F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	0.0280 in

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	3.7 @Frequency 100 Hz	3.7 @Frequency 100 Hz	ASTM D150

Electrical Properties	Metric	English	Comments
Dielectric Strength	30.0 kV/mm	760 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	232 - 243 °C	450 - 470 °F	
Middle Barrel Temperature	238 - 249 °C	460 - 480 °F	
Front Barrel Temperature	243 - 254 °C	470 - 490 °F	
Nozzle Temperature	243 - 254 °C	470 - 490 °F	
Melt Temperature	249 - 260 °C	480 - 500 °F	
Mold Temperature	82.2 - 121 °C	180 - 250 °F	
Drying Temperature	121 °C	250 °F	
Dry Time	<= 12 hour	<= 12 hour	
Moisture Content	<= 0.020 %	<= 0.020 %	
Injection Pressure	6.89 - 11.7 MPa	1000 - 1700 psi	
Back Pressure	0.138 - 0.414 MPa	20.0 - 60.0 psi	
Shot Size	40 - 80 %	40 - 80 %	
Screw Speed	40 - 80 rpm	40 - 80 rpm	

Descriptive Properties	Value	Comments
Holding Pressure	500 to 900 psi	
Injection Rate	Moderate-Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China