

Entec Hypro™ PPH-GF10 Natural Homopolymer Polypropylene, 10% Glass Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Glass Fiber Filler

Material Notes:

Information provided by Entec

Order this product through the following link:

http://www.lookpolymers.com/polymer_Entec-Hypro-PPH-GF10-Natural-Homopolymer-Polypropylene-10-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in ³	ASTM D792
Melt Flow	10.0 g/10 min @Load 2.16 kg, Temperature 230 °C	10.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	54.0 MPa	7830 psi	ASTM D638
Elongation at Break	6.00 %	6.00 %	ASTM D638
Elongation at Yield	3.00 %	3.00 %	ASTM D638
Flexural Strength	66.0 MPa	9570 psi	ASTM D790
Flexural Modulus	2.69 GPa	390 ksi	tangent; ASTM D790
Izod Impact, Notched	0.640 J/cm @Thickness 3.17 mm	1.20 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

