

Entec Hypro™ PPH-T10 Homopolymer Polypropylene, 10% Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Information provided by Entec

Order this product through the following link:

http://www.lookpolymers.com/polymer_Entec-Hypro-PPH-T10-Homopolymer-Polypropylene-10-Talc-Reinforced.php

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in³	ASTM D792
Melt Flow	10.0 g/10 min	10.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.0 MPa	4930 psi	ASTM D638
Elongation at Break	20.0 %	20.0 %	ASTM D638
Elongation at Yield	7.00 %	7.00 %	ASTM D638
Flexural Strength	40.0 MPa	5800 psi	ASTM D790
Flexural Modulus	1.862 GPa	270.1 ksi	tangent; ASTM D790
Izod Impact, Notched	0.320 J/cm	0.599 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	113 °C	235 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China