

Epoxyset Epoxibond EB-107LP-2 Unfilled Epoxy Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive

Material Notes:

A two-component, unfilled epoxy adhesive used for bonding and small potting applications in the medical, electronics, and aerospace industries. Information provided by Epoxyset Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Epoxyset-Epoxibond-EB-107LP-2-Unfilled-Epoxy-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	
Viscosity	300 - 600 cP	300 - 600 cP	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	86	86	ASTM D2240
Adhesive Bond Strength	19.3 MPa	2800 psi	Lap Shear Strength

Thermal Properties	Metric	English	Comments
CTE, linear	$\geq 50.0 \mu\text{m/m-}^{\circ}\text{C}$	$\geq 27.8 \mu\text{in/in-}^{\circ}\text{F}$	
Maximum Service Temperature, Air	120 °C	248 °F	
Minimum Service Temperature, Air	-55.0 °C	-67.0 °F	
Glass Transition Temp, Tg	65.0 °C	149 °F	

Optical Properties	Metric	English	Comments
Refractive Index	1.52	1.52	

Processing Properties	Metric	English	Comments
Cure Time	180 min	3.00 hour	
	@Temperature 65.0 °C	@Temperature 149 °F	
	1440 min	24.0 hour	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Pot Life	480 min	480 min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China