

Eurostar Star L PA6 D36 PA6, Injection Molded

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Star L PA6 D36 is a MOS2 Lubricated Unreinforced, Polyamide 6 Injection Molding Resin Information provided by Eurostar.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurostar-Star-L-PA6-D36-PA6-Injection-Molded.php

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.013 - 0.016 cm/cm @Thickness 4.00 mm	0.013 - 0.016 in/in @Thickness 0.157 in	E2P method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	80.0 MPa	11600 psi	ISO 527
Elongation at Yield	4.0 %	4.0 %	ISO 527
Flexural Yield Strength	100 MPa	14500 psi	2 mm/min; ISO 178
Flexural Modulus	3.20 GPa	464 ksi	ISO 178
Izod Impact, Notched (ISO)	3.80 kJ/m ²	1.81 ft-lb/in ²	80x10x4; ISO 180/1A
Izod Impact, Unnotched (ISO)	35.0 kJ/m ²	16.7 ft-lb/in ²	80x10x4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	Flatw 80x10x4, sp=64 mm; ISO 75/Af

Processing Properties	Metric	English	Comments
Zone 1	230 - 240 °C	446 - 464 °F	
Zone 2	235 - 245 °C	455 - 473 °F	
Zone 3	240 - 260 °C	464 - 500 °F	
Melt Temperature	240 - 260 °C	464 - 500 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	
Drying Temperature	75.0 - 85.0 °C @Time 14400 - 21600 sec	167 - 185 °F @Time 4.00 - 6.00 hour	

Moisture Content	0.20 %	0.20 %	
Processing Properties	Metric	English	Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China