

Eurostar Staramide AG10 PA66, 50% Glass Filled, Injection Molded

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 50% Glass Fiber Filled

Material Notes:

AG10 is a 50% Glass Fiber Reinforced Polyamide 66 Injection Molding Resin. Information provided by Polymer Technology & Services, the North American exclusive supplier.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurostar-Staramide-AG10-PA66-50-Glass-Filled-Injection-Molded.php

Physical Properties	Metric	English	Comments
Density	1.58 g/cc	0.0571 lb/in ³	ISO 1183
Moisture Absorption	0.700 % @Temperature 23.0 °C	0.700 % @Temperature 73.4 °F	50% RH; ISO 62
Water Absorption at Saturation	2.5 % @Temperature 23.0 °C	2.5 % @Temperature 73.4 °F	ISO 62-1
Linear Mold Shrinkage, Flow	0.0010 - 0.0025 cm/cm	0.0010 - 0.0025 in/in	on Tensile Bar; ISO 294

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	114	114	ISO 2039-2
Tensile Strength at Break	210 MPa	30500 psi	5 mm/min; ISO 527
Elongation at Break	3.0 %	3.0 %	5 mm/min; ISO 527
Tensile Modulus	14.8 GPa	2150 ksi	1 mm/min; ISO 527
Flexural Strength	310 MPa	45000 psi	2 mm/min; ISO 178
Flexural Modulus	13.8 GPa	2000 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	13.0 kJ/m ² @Temperature -30.0 °C	6.19 ft-lb/in ² @Temperature -22.0 °F	80x10x4; ISO 180/1A
	13.0 kJ/m ² @Temperature -40.0 °C	6.19 ft-lb/in ² @Temperature -40.0 °F	80x10x4; ISO 180/1A
	14.0 kJ/m ² @Temperature -20.0 °C	6.66 ft-lb/in ² @Temperature -4.00 °F	80x10x4; ISO 180/1A
	15.0 kJ/m ² @Temperature 23.0 °C	7.14 ft-lb/in ² @Temperature 73.4 °F	80x10x4; ISO 180/1A
Charpy Impact Unnotched	14.0 J/cm ²	66.6 ft-lb/in ²	Edgew 80x10x4 sp=62; ISO 179/1eU

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	19.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$ @Temperature 23.0 - 60.0 $^{\circ}\text{C}$	10.6 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$ @Temperature 73.4 - 140 $^{\circ}\text{F}$	ISO 11359-2
CTE, linear, Transverse to Flow	71.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$ @Temperature 23.0 - 60.0 $^{\circ}\text{C}$	39.4 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$ @Temperature 73.4 - 140 $^{\circ}\text{F}$	ISO 11359-2
Thermal Conductivity	0.330 W/m-K	2.29 BTU-in/hr-ft ² - $^{\circ}\text{F}$	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	262 $^{\circ}\text{C}$	504 $^{\circ}\text{F}$	Edgew 120x10x4, sp=100 mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	258 $^{\circ}\text{C}$	496 $^{\circ}\text{F}$	Edgew 120x10x4, sp=100 mm; ISO 75/Af
Vicat Softening Point	260 $^{\circ}\text{C}$	500 $^{\circ}\text{F}$	B/120; ISO 306
	260 $^{\circ}\text{C}$	500 $^{\circ}\text{F}$	B/50; ISO 306
UL RTI, Electrical	65.0 $^{\circ}\text{C}$ @Thickness 3.00 mm	149 $^{\circ}\text{F}$ @Thickness 0.118 in	
UL RTI, Mechanical with Impact	65.0 $^{\circ}\text{C}$ @Thickness 0.750 mm	149 $^{\circ}\text{F}$ @Thickness 0.0295 in	
	65.0 $^{\circ}\text{C}$ @Thickness 3.00 mm	149 $^{\circ}\text{F}$ @Thickness 0.118 in	
UL RTI, Mechanical without Impact	65.0 $^{\circ}\text{C}$ @Thickness 0.750 mm	149 $^{\circ}\text{F}$ @Thickness 0.0295 in	
	65.0 $^{\circ}\text{C}$ @Thickness 3.00 mm	149 $^{\circ}\text{F}$ @Thickness 0.118 in	
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	IEC 60695-11-10
	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	IEC 60695-11-10
Flame Spread	2.00 mm/min @Thickness 3.00 mm	0.0787 in/min @Thickness 0.118 in	FMVSS Buring Speed
	6.00 mm/min @Thickness 2.00 mm	0.236 in/min @Thickness 0.0787 in	FMVSS Buring Speed

Thermal Properties	Metric	English	Comments
Glow Wire Test	650 °C @Thickness 2.00 mm	1200 °F @Thickness 0.0787 in	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+16 ohm-cm	>= 1.00e+16 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+16 ohm	>= 1.00e+16 ohm	ROA; IEC 60093
Dielectric Constant	3.2 @Frequency 1.00e+6 Hz	3.2 @Frequency 1.00e+6 Hz	IEC 60250
	3.4 @Frequency 50.0 - 60.0 Hz	3.4 @Frequency 50.0 - 60.0 Hz	IEC 60250
Dielectric Strength	19.0 kV/mm @Thickness 3.20 mm	483 kV/in @Thickness 0.126 in	in oil; IEC 60243-1
	0.0068 @Frequency 50.0 - 60.0 Hz	0.0068 @Frequency 50.0 - 60.0 Hz	IEC 60250
Dissipation Factor	0.015 @Frequency 1.00e+6 Hz	0.015 @Frequency 1.00e+6 Hz	IEC 60250
	350 V	350 V	M; IEC 60112
Comparative Tracking Index	500 V	500 V	IEC 60112

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	260 - 280 °C	500 - 536 °F	Zone 1
Middle Barrel Temperature	270 - 280 °C	518 - 536 °F	Zone 2
Front Barrel Temperature	270 - 290 °C	518 - 554 °F	Zone 3
Melt Temperature	270 - 290 °C	518 - 554 °F	
Mold Temperature	60.0 - 90.0 °C	140 - 194 °F	
Drying Temperature	75.0 - 85.0 °C	167 - 185 °F	
Dry Time	4.00 - 6.00 hour	4.00 - 6.00 hour	
Moisture Content	0.20 %	0.20 %	

Processing Properties	Metric	English	Comments
Descriptive Properties		Value	Comments
Potable Water		ACS WRAS	
UL f1		f1	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China