

Eurostar Starflam RF0069 PA66, 30% Glass Fiber, Flame Retardant, Injection Molded

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Glass Fiber Filled, Flame Retardant

Material Notes:

Starflam RF0069 is a Flame Retardant, 30% Glass Reinforced Polyamide 66 Injection Molding Resin (also known as PA66 30V U2 Z79 or RF1006Z590) Information provided by Eurostar.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurostar-Starflam-RF0069-PA66-30-Glass-Fiber-Flame-Retardant-Injection-Molded.php

Physical Properties	Metric	English	Comments
Density	1.58 g/cc	0.0571 lb/in ³	ISO 1183
Water Absorption at Saturation	4.0 % @Temperature 23.0 °C	4.0 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0020 - 0.0030 cm/cm	0.0020 - 0.0030 in/in	on Tensile Bar; E2P method

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	108	108	ISO 2039-2
Tensile Strength at Break	165 MPa	23900 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	9.50 GPa	1380 ksi	1 mm/min; ISO 527
Flexural Strength	190 MPa	27600 psi	2 mm/min; ISO 178
Flexural Modulus	9.30 GPa	1350 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m ² @Temperature -20.0 °C	3.33 ft-lb/in ² @Temperature -4.00 °F	80x10x4; ISO 179/1eA
	8.00 kJ/m ² @Temperature 23.0 °C	3.81 ft-lb/in ² @Temperature 73.4 °F	80x10x4; ISO 179/1eA
Charpy Impact Unnotched	6.00 J/cm ²	28.6 ft-lb/in ²	Edgew 80x10x4 sp=62; ISO 179/1eU

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	23.0 µm/m-°C @Temperature 23.0 - 60.0 °C	12.8 µin/in-°F @Temperature 73.4 - 140 °F	ISO 11359-2
	72.0 µm/m-°C	40.0 µin/in-°F	

CTE, linear, Transverse to Flow Thermal Properties	Metric @ Temperature 23.0 - 60.0 °C	English @ Temperature 73.4 - 140 °F	ISO 11359-2 Comments
Hot Ball Pressure Test	123 - 127 °C	253 - 261 °F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	262 °C	504 °F	Edgew 120x10x4, sp=100 mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	248 °C	478 °F	Edgew 120x10x4, sp=100 mm; ISO 75/Ae
Vicat Softening Point	258 °C	496 °F	B/120; ISO 306
UL RTI, Electrical	65.0 °C	149 °F	
UL RTI, Mechanical with Impact	65.0 °C	149 °F	
UL RTI, Mechanical without Impact	65.0 °C	149 °F	
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
Oxygen Index	31 %	31 %	ISO 4589
Glow Wire Test	960 °C @Thickness 2.00 mm	1760 °F @Thickness 0.0787 in	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	250 V	250 V	IEC 60112

Processing Properties	Metric	English	Comments
Zone 1	270 - 290 °C	518 - 554 °F	
Zone 2	270 - 280 °C	518 - 536 °F	
Zone 3	270 - 280 °C	518 - 536 °F	
Melt Temperature	270 - 280 °C	518 - 536 °F	
Mold Temperature	70.0 - 100 °C	158 - 212 °F	
Drying Temperature	75.0 - 85.0 °C @Time 14400 - 21600 sec	167 - 185 °F @Time 4.00 - 6.00 hour	
Moisture Content	0.20 %	0.20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China