

Eurotec® Tecolen® CP20 GR40 NL PPCP, 40% glass fiber reinforced, natural

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Glass Fiber Filler

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecolen-CP20-GR40-NL-PPCP-40-glass-fiber-reinforced-natural.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ISO 527
Elongation at Break	5.0 %	5.0 %	ISO 527
Tensile Modulus	7.00 GPa	1020 ksi	ISO 527
Izod Impact, Notched (ISO)	15.0 kJ/m ²	7.14 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	25.0 kJ/m ²	11.9 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	160 - 165 °C	320 - 329 °F	[10 K/min], ISO 11357
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	ISO 75
Flammability, UL94	HB	HB	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	200 - 240 °C	392 - 464 °F	

Processing Properties	Metric	English	Comments
Feed Temperature	40-60.0 °C	104-140 °F	Typical
Mold Temperature	20.0 - 50.0 °C	68.0 - 122 °F	
Hold Pressure	40.0 - 80.0 MPa	5800 - 11600 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China