

Eurotec® Tecomid® NA40 GR40 NL PA 6.6 40% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Excellent stiffness/toughness balanceHigh mechanical strengthVery good thermal stabilityExcellent flammability characteristicsGood electrical propertiesHigh wear resistance and low frictionVery good chemical resistanceGood flow and processing properties
APPLICATIONS: AutomotiveElectrical/ElectronicFurnitureConstructionHome appliances

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NA40-GR40-NL-PA-66-40-glass-fiber-reinforced.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in ³	ISO 1183
Filler Content	40 %	40 %	ISO 3451
Moisture Absorption at Equilibrium	1.6 %	1.6 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	5.0 %	5.0 %	23°C; ISO 62
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	215 MPa	31200 psi	ISO 527
Elongation at Break	3.0 %	3.0 %	ISO 527
Tensile Modulus	13.0 GPa	1890 ksi	ISO 527
Flexural Strength	300 MPa	43500 psi	ISO 178
Flexural Modulus	11.0 GPa	1600 ksi	ISO 178
Izod Impact, Notched (ISO)	12.0 kJ/m ²	5.71 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	15.0 kJ/m ²	7.14 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	8.00 J/cm ²	38.1 ft-lb/in ²	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	9.00 J/cm ²	42.8 ft-lb/in ²	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Mechanical Properties	1.30 J/cm ² Metric	6.19 ft-lb/in ² English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.60 J/cm ²	7.61 ft-lb/in ²	ISO 179/eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	260 °C	500 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	255 °C	491 °F	ISO 75-1/2
Vicat Softening Point	255 °C	491 °F	50N; ISO 306
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	650 °C	1200 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	500 V	500 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China