

Eurotec® Tecomid® NA40 MR15 NL IL PA 6.6 15% mineral reinforced, impact modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Excellent stiffness/toughness balanceHigh mechanical strengthVery good thermal stabilityExcellent flammability characteristicsGood electrical propertiesHigh wear resistance and low frictionVery good chemical resistanceGood flow and processing properties
APPLICATIONS: AutomotiveElectrical/ElectronicFurnitureConstructionHome appliances

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NA40-MR15-NL-IL-PA-66-15-mineral-reinforced-impact-modified.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in ³	ISO 1183
Filler Content	15 %	15 %	ISO 3451
Moisture Absorption at Equilibrium	2.0 %	2.0 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	7.5 %	7.5 %	23°C; ISO 62
Linear Mold Shrinkage	0.014 cm/cm	0.014 in/in	
Linear Mold Shrinkage, Transverse	0.014 cm/cm	0.014 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	75.0 MPa	10900 psi	ISO 527
Tensile Modulus	3.75 GPa	544 ksi	ISO 527
Izod Impact, Notched (ISO)	7.00 kJ/m ²	3.33 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	9.00 kJ/m ²	4.28 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	10.0 J/cm ²	47.6 ft-lb/in ²	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	12.5 J/cm ²	59.5 ft-lb/in ²	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179/eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.00 J/cm ²	4.76 ft-lb/in ²	

Mechanical Properties	Metric	English	ISO 179/eA Comments
	@ Temperature 23.0 °C	@ Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	ISO 75-1/2
Vicat Softening Point	240 °C	464 °F	50N; ISO 306
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	650 °C	1200 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	500 V	500 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China