

Eurotec® Tecomid® NA40 NL FA 50 PA 6.6 unreinforced, UL94 V0, halogen/phosphorus free

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Excellent stiffness/toughness balanceHigh mechanical strengthVery good thermal stabilityExcellent flammability characteristicsGood electrical propertiesHigh wear resistance and low frictionVery good chemical resistanceGood flow and processing properties
APPLICATIONS: AutomotiveElectrical/ElectronicFurnitureConstructionHome appliances

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NA40-NL-FA-50-PA-66-unreinforced-UL94-V0-halogenphosphorus-free.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Filler Content	0.00 %	0.00 %	ISO 3451
Moisture Absorption at Equilibrium	2.2 %	2.2 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	7.0 %	7.0 %	23°C; ISO 62
Linear Mold Shrinkage	0.013 cm/cm	0.013 in/in	
Linear Mold Shrinkage, Transverse	0.013 cm/cm	0.013 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ISO 527
Tensile Modulus	3.75 GPa	544 ksi	ISO 527
Izod Impact, Notched (ISO)	3.00 kJ/m ²	1.43 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	4.00 kJ/m ²	1.90 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	4.50 J/cm ²	21.4 ft-lb/in ²	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.300 J/cm ²	1.43 ft-lb/in ²	ISO 179/eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.400 J/cm ²	1.90 ft-lb/in ²	

Mechanical Properties	Metric	English	ISO 179/eA Comments
	@ Temperature 23.0 °C	@ Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	225 °C	437 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ISO 75-1/2
Vicat Softening Point	245 °C	473 °F	50N; ISO 306
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	960 °C	1760 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	600 V	600 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China