

Eurotec® Tecomid® NA40 NL IL PA 6.6 impact modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Excellent stiffness/toughness balanceHigh mechanical strengthVery good thermal stabilityExcellent flammability characteristicsGood electrical propertiesHigh wear resistance and low frictionVery good chemical resistanceGood flow and processing properties
APPLICATIONS: AutomotiveElectrical/ElectronicFurnitureConstructionHome appliances

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NA40-NL-IL-PA-66-impact-modified.php

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in ³	ISO 1183
Filler Content	0.00 %	0.00 %	ISO 3451
Moisture Absorption at Equilibrium	2.2 %	2.2 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	6.5 %	6.5 %	23°C; ISO 62
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	
Linear Mold Shrinkage, Transverse	0.015 cm/cm	0.015 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	ISO 527
Elongation at Yield	5.0 %	5.0 %	ISO 527
Tensile Modulus	2.30 GPa	334 ksi	ISO 527
Izod Impact, Notched (ISO)	15.0 kJ/m ²	7.14 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	30.0 kJ/m ²	14.3 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	NB	NB	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179/eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	3.50 J/cm ²	16.7 ft-lb/in ²	

Mechanical Properties	Metric	English	ISO 179/eA Comments
	@ Temperature 23.0 °C	@ Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	10 K/min; ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	70.0 °C	158 °F	ISO 75-1/2
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	600 V	600 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China