

Eurotec® Tecomid® NB40 GR30 NL IH PA 6 30% glass fiber reinforced, impact modified

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Excellent stiffness/toughness balanceHigh mechanical strengthVery good thermal stabilityExcellent flammability characteristicsGood electrical propertiesHigh wear resistance and low frictionVery good chemical resistanceGood flow and processing properties
APPLICATIONS: AutomotiveElectrical/ElectronicFurnitureConstructionHome appliances

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NB40-GR30-NL-IH-PA-6-30-glass-fiber-reinforced-impact-modified.php

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in ³	ISO 1183
Filler Content	30 %	30 %	ISO 3451
Moisture Absorption at Equilibrium	1.8 %	1.8 %	Humidity Absorption, 50% RH, 23°C; ISO 62
Water Absorption at Saturation	5.5 %	5.5 %	23°C; ISO 62
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	140 MPa	20300 psi	ISO 527
Elongation at Break	4.0 %	4.0 %	ISO 527
Tensile Modulus	6.50 GPa	943 ksi	ISO 527
Flexural Strength	180 MPa	26100 psi	ISO 178
Flexural Modulus	5.50 GPa	798 ksi	ISO 178
Izod Impact, Notched (ISO)	14.0 kJ/m ²	6.66 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	22.0 kJ/m ²	10.5 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	9.50 J/cm ²	45.2 ft-lb/in ²	ISO 179/eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	10.5 J/cm ²	50.0 ft-lb/in ²	ISO 179/eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	1.50 J/cm ²	1.14 ft-lb/in ²	ISO 179/eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	2.40 J/cm ²	11.4 ft-lb/in ²	ISO 179/eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	223 °C	433 °F	10 K/min; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75-1/2
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	ISO 75-1/2
Vicat Softening Point	200 °C	392 °F	50N; ISO 306
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	650 °C	1200 °F	plaque; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	500 V	500 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China