

Eurotec® Tecomid® NB40 NL FY50 PA6, unfilled, flame retardant - halogen & red phosphorus free, natural

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced, Flame Retardant

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NB40-NL-FY50-PA6-unfilled-flame-retardant-halogen-red-phosphorus-free-natural.php

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in ³	ISO 1183
Moisture Absorption	2.70 % @Temperature 23.0 °C	2.70 % @Temperature 73.4 °F	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.011 cm/cm	0.011 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	70.0 MPa	10200 psi	ISO 527
Tensile Modulus	3.25 GPa	471 ksi	ISO 527
Izod Impact, Notched (ISO)	6.00 kJ/m ² @Temperature -30.0 °C	2.86 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	7.00 kJ/m ² @Temperature 23.0 °C	3.33 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A

Thermal Properties	Metric	English	Comments
Melting Point	223 °C	433 °F	[10 K/min], ISO 11357
Deflection Temperature at 0.46 MPa (66 psi)	185 °C	365 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	ISO 75
Vicat Softening Point	200 °C @Load 5.10 kg	392 °F @Load 11.2 lb	ISO 306
Flammability, UL94	V-2 @Thickness 1.60 mm	V-2 @Thickness 0.0630 in	

Thermal Properties	V-2 Metric	V-2 English	Comments
	@Thickness 0.750 mm	@Thickness 0.0295 in	
Glow Wire Test	775 °C	1430 °F	GWIT; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	960 °C	1760 °F	GWFI; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	600 V	600 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	230 - 250 °C	446 - 482 °F	
Feed Temperature	60.0 - 80.0 °C	140 - 176 °F	Throat
Mold Temperature	40.0 - 90.0 °C	104 - 194 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	ISO 960
Hold Pressure	50.0 - 100 MPa	7250 - 14500 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China