

Eurotec® Tecomid® NB40 NL IH PA6, impact modified, natural

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Impact Grade

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecomid-NB40-NL-IH-PA6-impact-modified-natural.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ISO 1183
Moisture Absorption	2.30 %	2.30 %	50% RH; ISO 62
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Linear Mold Shrinkage, Flow	0.015 cm/cm	0.015 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.015 cm/cm	0.015 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	45.0 MPa	6530 psi	ISO 527
Tensile Modulus	1.50 GPa	218 ksi	ISO 527
Izod Impact, Notched (ISO)	25.0 kJ/m ²	11.9 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	75.0 kJ/m ²	35.7 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched (ISO)	NB	NB	ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	ISO 180/1U
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	223 °C	433 °F	[10 K/min], ISO 11357
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	ISO 75
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	

Thermal Properties	Metric @ Thickness 0.750 mm	English @ Thickness 0.0295 in	Comments
--------------------	--------------------------------	----------------------------------	----------

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Comparative Tracking Index	600 V	600 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	230 - 250 °C	446 - 482 °F	
Feed Temperature	60.0 - 80.0 °C	140 - 176 °F	Throat
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Moisture Content	<= 0.20 %	<= 0.20 %	ISO 960
Hold Pressure	50.0 - 100 MPa	7250 - 14500 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China