

Eurotec® Tecotek® PC30 NL TD 700 PC, unfilled, flame retardant - halogen (RoHS compliant), impact modified, natural

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Impact Modified , Polycarbonate, Unreinforced, Flame Retardant

Material Notes:

Information provided by Eurotec®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Eurotec-Tecotek-PC30-NL-TD-700-PC-unfilled-flame-retardant-halogen-RoHS-compliant-impact-modified-natural.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ISO 1183
Moisture Absorption	0.200 % @Temperature 23.0 °C	0.200 % @Temperature 73.4 °F	50% RH; ISO 960
Linear Mold Shrinkage, Flow	0.0060 cm/cm	0.0060 in/in	Eurotec
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	Eurotec

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	ISO 527
Elongation at Break	>= 50 %	>= 50 %	ISO 527
Tensile Modulus	2.25 GPa	326 ksi	ISO 527
Izod Impact, Notched (ISO)	20.0 kJ/m ² @Temperature -30.0 °C	9.52 ft-lb/in ² @Temperature -22.0 °F	ISO 180/1A
	50.0 kJ/m ² @Temperature 23.0 °C	23.8 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 180/1U
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	105 °C	221 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	ISO 75

Thermal Properties	130 °C Metric	266 °F English	Comments
	@Load 5.10 kg	@Load 11.2 lb	
Flammability, UL94	V-0	V-0	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	900 °C	1650 °F	GWIT; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	960 °C	1760 °F	GWFI; IEC 60695
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093
Comparative Tracking Index	225 V	225 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	250 - 290 °C	482 - 554 °F	
Feed Temperature	60.0 - 80.0 °C	140 - 176 °F	Throat
Mold Temperature	80.0 - 100 °C	176 - 212 °F	
Drying Temperature	120 °C	248 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	
Moisture Content	<= 0.10 %	<= 0.10 %	ISO 960
Hold Pressure	60.0 - 120 MPa	8700 - 17400 psi	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Injection Speed	Medium - Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China