

ExxonMobil ENABLE™ EN 33900 Adhesive and Sealant Applications Resin (discontinued **)

Category : Polymer , Adhesive , Thermoplastic , Ethylene Butyl Acrylate

Material Notes:

Enable EN 33900 is a high flow, 32.5% nBA copolymer suitable for use in hot melt adhesives and sealants. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-ENABLE-EN-33900-Adhesive-and-Sealant-Applications-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.921 g/cc	0.0333 lb/in³	ExxonMobil Method
Viscosity	8340 cP @Temperature 190 °C	8340 cP @Temperature 374 °F	ASTM D3236
Butyl Acrylate Content	32.5 %	32.5 %	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	44	44	15s; ASTM D2240
Tensile Strength at Break	0.965 MPa	140 psi	ASTM D638
Elongation at Break	135 %	135 %	ASTM D638
Flexural Modulus	0.00538 GPa	0.780 ksi	1% secant; ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	60.0 °C	140 °F	Peak Melting Temperature; ExxonMobil Method

Descriptive Properties	Value	Comments
Features	Thermal Stabilizer	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China