

ExxonMobil EXXPRO™ 3035 Low Cure Activity Grade

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Exxpro Elastomer is a brominated copolymer of isobutylene and paramethylstyrene. The product form is off white to amber bales. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-EXXPRO-3035-Low-Cure-Activity-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.920 g/cc	0.920 g/cc	
Mooney Viscosity	40 - 50	40 - 50	ML 1 + 8; ASTM D1646
	@Temperature 125 °C	@Temperature 257 °F	
	45	45	ML 1 + 8, Target; ASTM D1646
	@Temperature 125 °C	@Temperature 257 °F	
Maximum Moisture Content	0.30	0.30	

Component Elements Properties	Metric	English	Comments
Calcium, Ca	0.090 %	0.090 %	Target
	0.070 - 0.11 %	0.070 - 0.11 %	

Descriptive Properties	Value	Comments
Bromine	0.42-0.52%	mol %
	0.47%	mol %, Target

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China