

ExxonMobil Escorene™ FL 00328 Ethylene Vinyl Acetate Copolymer (European Grade)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

Material Notes:

Product Description: FL 00328 is a copolymer of ethylene and vinyl acetate offering low gel. **Processing Conditions:** Processing temperatures above 220°C (428°F) may cause resin degradation. Machines should always be completely purged with LDPE or suitable cleaning compound before shutdown. **Availability:** Africa & Middle East, Asia Pacific and Europe **Additive:** Antiblock: NoSlip: NoThermal Stabilizer: No **Applications:**Co-Extrusion FilmsCompoundingFabric CoatingSheet ExtrusionInformation provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-FL-00328-Ethylene-Vinyl-Acetate-Copolymer-European-Grade.php

Physical Properties	Metric	English	Comments
Density	0.951 g/cc	0.0344 lb/in³	ExxonMobil method
Vinyl Acetate Content	27 %	27 %	ExxonMobil method
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	81 @Time 15.0 sec	81 @Time 0.00417 hour	Molded Properties; ISO 868
Tensile Strength at Break	>= 0.689 MPa	>= 100 psi	Molded Properties; ISO 527-2/1A/100
Tensile Modulus	0.0159 GPa	2.30 ksi	Molded Properties; ISO 527-2/1

Thermal Properties	Metric	English	Comments
Melting Point	<= 160 °C	<= 320 °F	Peak Melting Point; ExxonMobil method
Vicat Softening Point	44.4 °C	112 °F	ASTM D1525

Descriptive Properties	Value	Comments
Blending Temperature	220	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China