

ExxonMobil Escorene® LL-3113 LLDPE/Hexene Premium High Strength, 0.7 mil Film (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Hexene, Film Grade

Material Notes:

Data provided by the manufacturer, Exxon Chemical. An LLDPE hexene copolymer film resin. Films made from this resin have outstanding tensile, stiffness and toughness properties. These superior properties along with the resin's good drawdown capability permit usage in many demanding packaging applications. Applications: Merchandise bags; Frozen food packaging; Heavy duty bags; Sandwich bags; Liners. Data for film properties below based on 0.7 mil film.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Escorene-LL-3113-LLDPEHexene-Premium-High-Strength-07-mil-Film-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.921 g/cc	0.0333 lb/in ³	Exxon Method
Thickness	17.8 microns	0.700 mil	
Melt Flow	1.3 g/10 min	1.3 g/10 min	Exxon Method

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	11.4 MPa	1650 psi	ASTM D882
Film Tensile Strength at Yield, TD	11.9 MPa	1730 psi	ASTM D882
Film Elongation at Break, MD	480 %	480 %	ASTM D882
Film Elongation at Break, TD	690 %	690 %	ASTM D882
Secant Modulus, MD	0.226 GPa	32.8 ksi	ASTM D882
Secant Modulus, TD	0.276 GPa	40.0 ksi	ASTM D882
Elmendorf Tear Strength MD	190 g	190 g	ASTM D1922
Elmendorf Tear Strength TD	720 g	720 g	ASTM D1922
Elmendorf Tear Strength, MD	10.7 g/micron	271 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	40.51 g/micron	1029 g/mil	ASTM D1922
Dart Drop	5.63 g/micron	143 g/mil	F50; ASTM D1709
Dart Drop Test	100 g	0.221 lb	F50; ASTM D-1709
Film Tensile Strength at Break, MD	57.6 MPa	8350 psi	ASTM D882
Film Tensile Strength at Break, TD	38.6 MPa	5600 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	126 °C	259 °F	Exxon Method

Optical Properties	Metric	English	Comments
Haze	30.4 %	30.4 %	ASTM D1003
Gloss	24 %	24 %	45°, ASTM D-2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China