

ExxonMobil Exxtral™ BMV 201 Performance Polyolefin

Category : Polymer , Thermoplastic , Ethylene Butyl Acrylate

Material Notes:

Product Description: A specialty thermoplastic olefin injection molding compound resin with good flow, cold temperature impact resistance, low CLTE, and excellent paintability for large automotive exterior parts including bumper fascia and rocker panels. **Availability:** North America **Features:** Ductile Good UV Resistance High Flow High Scratch Resistance Low Temperature Impact Resistance Paintable **Uses:** Automotive Applications Automotive Bumper Automotive Exterior Trim **Processing Method:** Injection Molding **Information provided by** ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Exxtral-BMV-201-Performance-Polyolefin.php

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in ³	ISO 1183/A
Melt Flow	26 g/10 min	26 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	19.0 MPa	2760 psi	ISO 527-2
Flexural Modulus	1.69 GPa	245 ksi	0.079 in/min; ISO 178
Izod Impact, Notched (ISO)	39.9 kJ/m ²	19.0 ft-lb/in ²	ISO 180/A
Dart Drop, Total Energy	26.0 J	19.2 ft-lb	7.22 ft/sec; ASTM D3763
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	0.504 µm/m-°C	0.280 µin/in-°F	ASTM E831
	@Temperature -30.0 - 100 °C	@Temperature -22.0 - 212 °F	
Deflection Temperature at 1.8 MPa (264 psi)	55.0 °C	131 °F	ISO 75-2/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China