

ExxonMobil Exxtral™ CMU 201 Performance Polyolefin

Category : Polymer , Thermoplastic , Ethylene Butyl Acrylate

Material Notes:

Product Description: A specialty thermoplastic polyolefin resin designed for automotive interior covered applications such as retainers in which a good stiffness toughness balance is required. **Availability:** Africa & Middle East, Asia Pacific, Europe, South America and North

America Features: Balanced Stiffness/Toughness Good Creep Resistance Good Dimensional Stability Good Mold Release Low Warpage **Uses:**

Automotive Applications: Automotive Interior Parts Automotive Interior Trim Automotive Under the Hood **Processing Method:** Injection

Molding Information provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Exxtral-CMU-201-Performance-Polyolefin.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	ISO 1183
Melt Flow	15 g/10 min	15 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	19.0 MPa	2760 psi	ISO 527-2/50
Tensile Strength, Yield	25.0 MPa	3630 psi	ISO 527-2/50
Elongation at Break	23 %	23 %	ISO 527-2/50
Elongation at Yield	3.0 %	3.0 %	ISO 527-2/50
Tensile Modulus	2.35 GPa	341 ksi	Secant; ISO 527-2/50
Charpy Impact, Notched	0.294 J/cm ²	1.40 ft-lb/in ²	Complete Break; ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.315 J/cm ²	1.50 ft-lb/in ²	Complete Break; ISO 179
	@Temperature 0.000 °C	@Temperature 32.0 °F	
	0.462 J/cm ²	2.20 ft-lb/in ²	Complete Break; ISO 179
	@Temperature 22.8 °C	@Temperature 73.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	ISO 75-2/A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China