

ExxonMobil Exxtral™ CNU 017 Performance Polyolefin

Category : Polymer , Thermoplastic , Ethylene Butyl Acrylate

Material Notes:

Product Description: A specialty thermoplastic polyolefin resin characterized by high flow, high stiffness, low odor and emissions that is typically used automotive air conditioning units. **Availability:** Africa & Middle East, Asia Pacific, Europe, South America and North America

Features: Balanced Stiffness/Toughness Good Impact Resistance Good Surface Finish Low Emissions Low to No Odor **Uses:** Automotive

Applications: Automotive Interior Parts Automotive Interior Trim **Processing Method:** Injection Molding **Information provided by ExxonMobil**

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Exxtral-CNU-017-Performance-Polyolefin.php

Physical Properties	Metric	English	Comments
Density	0.911 g/cc	0.0329 lb/in ³	ISO 1183
Melt Flow	15 g/10 min @Load 2.16 kg, Temperature 230 °C	15 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	18.0 MPa	2610 psi	ISO 527-2/50
Tensile Strength, Yield	31.0 MPa	4500 psi	ISO 527-2/50
Elongation at Break	35 %	35 %	ISO 527-2/50
Elongation at Yield	4.4 %	4.4 %	ISO 527-2/50
Tensile Modulus	1.75 GPa	254 ksi	Secant; ISO 527-2
Charpy Impact, Notched	0.357 J/cm ² @Temperature 0.000 °C	1.70 ft-lb/in ² @Temperature 32.0 °F	Complete Break; ISO 179
	0.567 J/cm ² @Temperature 22.8 °C	2.70 ft-lb/in ² @Temperature 73.0 °F	Complete Break; ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	219 °F	ISO 75-2/B
Deflection Temperature at 1.8 MPa (264 psi)	53.9 °C	129 °F	ISO 75-2/A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China