

ExxonMobil HD 7925.30 Barrier Film Resin

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Film Grade

Material Notes:

Product Description: HD 7925.30 is a medium molecular weight HDPE homopolymer for use in blown and cast film applications. Typical applications include those with low WVTR and clarity requirements.Availability: Latin America, North America and South America Additive: Antiblock: NoSlip: NoThermal Stabilizer: Yes Applications: Barrier Food PackagingBlown FilmFood packagingHeavy Duty BagsOriented Film ProductsSkin Layer for OPPStand Up PouchesInformation provided by ExxonMobil Chemical

Order this product through the following link:
http://www.lookpolymers.com/polymer_ExxonMobil-HD-792530-Barrier-Film-Resin.php

Physical Properties	Metric	English	Comments
Density	0.964 g/cc	0.0348 lb/in³	ExxonMobil Method
Thickness	25.4 microns	1.00 mil	
Melt Flow	2.40 g/10 min @Load 2.16 kg, Temperature 190 °C	2.40 g/10 min @Load 4.76 lb, Temperature 374 °F	ExxonMobil Method

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	31.72 MPa	4600 psi	ASTM D882
Film Tensile Strength at Yield, TD	27.58 MPa	4000 psi	ASTM D882
Film Elongation at Break, MD	790 %	790 %	ASTM D882
Film Elongation at Break, TD	6.0 %	6.0 %	ASTM D882
Elmendorf Tear Strength MD	9.0 g	9.0 g	ASTM D1922
Elmendorf Tear Strength TD	200 g	200 g	ASTM D1922
Dart Drop Test	50.0 g	0.110 lb	ASTM D1790
Film Tensile Strength at Break, MD	43.44 MPa	6300 psi	ASTM D882
Film Tensile Strength at Break, TD	38.61 MPa	5600 psi	ASTM D882
1% Secant Modulus, MD	1030 MPa	150000 psi	ASTM D882
1% Secant Modulus, TD	1520 MPa	220000 psi	ASTM D882

Descriptive Properties	Value	Comments
Features	Thermal Stabilizer	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China