

ExxonMobil HD 7960.13 HMW Blown Film Resin

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Film Grade

Material Notes:

Product Description: HD 7960.13 is a high molecular weight HDPE blown film resin. Films made from HD 7960.13 exhibit excellent impact and toughness properties, as well as high stiffness. HD 7960.13 is particularly recommended for films less than 0.5 mil in thickness.
Availability: Latin America, North America and South America
Additive: Antiblock: NoSlip: NoThermal Stabilizer: Yes
Applications: Blown FilmGrocery SacksInstitutional Can LinersMerchandise BagsProduce Bags on a RollTrash BagsInformation provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-HD-796013-HMW-Blown-Film-Resin.php

Physical Properties	Metric	English	Comments
Density	0.952 g/cc	0.0344 lb/in ³	ExxonMobil Method
Melt Flow	0.60 g/10 min	0.60 g/10 min	ExxonMobil Method
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	
High Load Melt Index	10 g/10 min	10 g/10 min	ASTM D1238
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	37.9 MPa	5500 psi	ASTM D882
Film Tensile Strength at Yield, TD	33.1 MPa	4800 psi	ASTM D882
Film Elongation at Break, MD	270 %	270 %	ASTM D882
Film Elongation at Break, TD	380 %	380 %	ASTM D882
Elmendorf Tear Strength MD	7.0 g	7.0 g	ASTM D1922
Elmendorf Tear Strength TD	30 g	30 g	ASTM D1922
Dart Drop	23.6 g/micron	600 g/mil	ASTM D1709
Dart Drop Test	300 g	0.662 lb	ASTM D1709A
Film Tensile Strength at Break, MD	82.7 MPa	12000 psi	ASTM D882
Film Tensile Strength at Break, TD	68.9 MPa	10000 psi	ASTM D882
1% Secant Modulus, MD	1030 MPa	150000 psi	ASTM D882
1% Secant Modulus, TD	1100 MPa	160000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	131 °C	267 °F	Peak Melting Temperature; ExxonMobil Method

Descriptive Properties	Value	Comments
Features	Thermal Stabilizer	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China