

ExxonMobil LDPE LD 617.LN Low Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

Product Description: LD 617.LN is a high flow, low density polyethylene homopolymer resin designed to provide excellent processability, flexibility and surface appearance. This multipurpose resin is performance engineered for applications such as housewares, overcaps and closures and concentrates. **Availability:** Latin America, North America and South America **Additive:** Antiblock: NoSlip: NoThermal Stabilizer: **NoApplications:** CapsClosuresCompoundingFood Packaging ContainersHouseware ArticlesInjection MoldingLabwareMasterbatch Base ResinInformation provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LDPE-LD-617LN-Low-Density-Polyethylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.919 g/cc	0.0332 lb/in ³	ExxonMobil method
Melt Flow	26 g/10 min	26 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	86	86	ASTM D2240
	@Time 15.0 sec	@Time 0.00417 hour	
Hardness, Shore D	42	42	ASTM D2240
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength at Break	7.58 MPa	1100 psi	ASTM D638
Tensile Strength, Yield	11.0 MPa	1600 psi	ASTM D638
Elongation at Break	120 %	120 %	ASTM D638
Elongation at Yield	30 %	30 %	ASTM D638
Flexural Modulus, 1% Secant	234 MPa	34000 psi	ASTM D790
Dart Drop, Total Energy	16.3 J	12.0 ft-lb	ASTM D3763
	@Temperature 22.8 °C	@Temperature 73.0 °F	
	19.0 J	14.0 ft-lb	ASTM D3763
	@Temperature -20.0 °C	@Temperature -4.00 °F	

Thermal Properties	Metric	English	Comments
			Peak Melting Point; ExxonMobil

Melting Point Thermal Properties	<= 230 °C Metric	<= 446 °F English	method Comments
Vicat Softening Point	83.9 °C	183 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China