

ExxonMobil LL 8360 Rotational Molding Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Rotational Molding Grade

Material Notes:

LL 8360 is a linear low density hexene copolymer designed to provide good processability along with outstanding dimensional control and low warpage. This resin is ideally suited for applications that require excellent processability and ESCR along with optimum balance of stiffness and low temperature toughness. Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LL-8360-Rotational-Molding-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.932 g/cc	0.0337 lb/in ³	ASTM D4883
ESCR 100% Igepal®	>= 1000 hour	>= 1000 hour	ASTM D1693
ESCR 10% Igepal®	650 hour	650 hour	ASTM D1693
Melt Flow	5.2 g/10 min	5.2 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	15.2 MPa	2200 psi	ASTM D638
Elongation at Yield	20.6 %	20.6 %	ASTM D638
Flexural Modulus	0.600 GPa	87.0 ksi	1% secant; ASTM D790
Impact Test	88.1 J	65.0 ft-lb	ARM
	@Thickness 3.17 mm, Temperature -40.0 °C	@Thickness 0.125 in, Temperature -40.0 °F	
	217 J	160 ft-lb	ARM
	@Thickness 6.35 mm, Temperature -40.0 °C	@Thickness 0.250 in, Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	125 °C	257 °F	ASTM D3418
Crystallization Temperature	111.2 °C	232.2 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	55.0 °C	131 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	37.0 °C	98.6 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China