

ExxonMobil LLDPE LL 5252.09 Linear Low Density Polyethylene Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Product Description: LL 5252.09 is a linear low density polyethylene resin designed to provide good processability and ease of blending.

The granular form of LL 5252.09 makes for efficient blending with pigments, slip and antiblock additives. Availability: Latin America, North

America and South America Additive: Antiblock: NoSlip: NoProcessing Aid: No Thermal Stabilizer: Yes Applications: Masterbatch Base

Resin Information provided by ExxonMobil

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-LLDPE-LL-525209-Linear-Low-Density-Polyethylene-Resin.php

Physical Properties	Metric	English	Comments
Density	0.926 g/cc	0.0335 lb/in ³	ExxonMobil method
Melt Flow	52 g/10 min @Load 2.16 kg, Temperature 190 °C	52 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	51 @Time 15.0 sec	51 @Time 0.00417 hour	ASTM D2240
Tensile Strength at Break	7.58 MPa	1100 psi	ASTM D638
Tensile Strength, Yield	15.2 MPa	2200 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Flexural Modulus, 1% Secant	448 MPa	65000 psi	ASTM D638
Izod Impact, Notched	4.43 J/cm	8.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	<= 252 °C	<= 486 °F	Peak Melting Point; ExxonMobil method
Brittleness Temperature	<= -76.1 °C	<= -105 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China