

ExxonMobil Mytex™ AS65KW-LGDC

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Talc filled compounded polypropylene produced for automotive interior applicationsInformation provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Mytex-AS65KW-LGDC.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in³	
Melt Flow	20 g/10 min	20 g/10 min	
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	75	75	
Tensile Strength, Yield	22.00 MPa	3191 psi	2 in/min; LAB032
Flexural Modulus	2.400 GPa	348.1 ksi	1% tangent, 0.05 in/min.; LAB033
Izod Impact, Notched	1.98 J/cm	3.70 ft-lb/in	LAB034

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	115 °C	239 °F	LAB036

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China