

ExxonMobil Santoprene® 101-87 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

A hard, black, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and completely recyclable. Key Features: UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component. Although not NSF certified, this product has a Material Supplier Form on file with NSF to facilitate its evaluation for use in applications requiring NSF certification. Recommended for applications requiring excellent flex fatigue resistance. Excellent ozone resistance. EU and China RoHS compliant. Applications: Automotive - Air Induction System Ducts, Boots and Bellows for Steering and Suspension, Plugs, Bumpers, Grommets, Clips, Seals, Gaskets and Weather Seals Consumer - Electronic and Floor Care Industrial - Seals and Gaskets Tubing Uses: Appliance Components Consumer Applications Gaskets Automotive Applications Diaphragms Seals Automotive Under the Hood Electrical Parts Tubing Availability: Africa & Middle East, Europe, North America, Asia Pacific, Latin America and South America Information provided by ExxonMobil Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Santoprene-101-87-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.960 g/cc	0.960 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	93	93	2 mm, 15 sec; ISO 868
	95	95	Air at 302°F, 168 hr; ASTM D573
Tensile Strength at Break	14.94 MPa	2168 psi	Air at 302°F, 168 hr; ASTM D573
	17.6 MPa	2550 psi	Across Flow; ASTM D412
Tensile Stress	7.10 MPa	1030 psi	ASTM D412
	@Strain 100 %	@Strain 100 %	
Elongation at Break	487.2 %	487.2 %	Air at 302°F, 168 hr; ASTM D573
	580 %	580 %	Across Flow; ASTM D412
Tear Strength	52.1 kN/m	297 pli	73°C, Die C; ASTM D624
Compression Set	36 %	36 %	158°F, 22 hr; ASTM D395
	44 %	44 %	257°F, 70 hr; ASTM D395

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-53.9 °C	-65.0 °F	ASTM D746
UL RTI, Electrical	90.0 °C	194 °F	UL 746
UL RTI, Mechanical with Impact	90.0 °C	194 °F	UL 746
	@Thickness 25.4 mm	@Thickness 1.00 in	
	90.0 °C	194 °F	UL 746
	@Thickness 38.1 mm	@Thickness 1.50 in	
	95.0 °C	203 °F	UL 746
	@Thickness 76.2 mm	@Thickness 3.00 in	
Flammability, UL94	HB	HB	
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.6	2.6	1.98 mm; ASTM D150
Dielectric Strength	29.5 kV/mm	750 kV/in	2.03 mm; ASTM D149

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	
Rear Barrel Temperature	182 °C	360 °F	
Middle Barrel Temperature	188 °C	370 °F	
Front Barrel Temperature	193 °C	380 °F	
Nozzle Temperature	199 - 235 °C	390 - 455 °F	
Die Temperature	210 °C	410 °F	Extrusion
Melt Temperature	204 °C	400 °F	Extrusion
	204 - 232 °C	400 - 450 °F	Processing
Mold Temperature	10.0 - 51.7 °C	50.0 - 125 °F	Processing

Drying Temperature Processing Properties	82.2 °C Metric	180 °F English	Comments
Dry Time	3 hour	3 hour	
Moisture Content	0.080 %	0.080 %	
Back Pressure	0.345 - 0.689 MPa	50.0 - 100 psi	Processing
	5.00 - 20.0 MPa	725 - 2900 psi	Extrusion
Clamp Pressure	41.4 - 68.9 MPa	6000 - 10000 psi	
Vent Depth	0.00254 cm	0.00100 in	
Cushion	0.317 - 0.635 cm	0.125 - 0.250 in	
Screw Speed	100 - 200 rpm	100 - 200 rpm	

Descriptive Properties	Value	Comments
Color	Black	
Form	Pellets	
Injection Rate	Fast	
Maximum Regrind %	20	
Screw Compression Ratio	2:1 - 2.5:1	
Screw L/D Ratio	16:1 - 20:1	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China