

ExxonMobil Thermrex Series V-32

Category : Fluid , Quenchant

Material Notes:

The Thermrex Series is a family of four quench oils for the heat treatment of alloy steels. They are comprised of selected additives and solvent-refined base stocks to provide optimum chemical and thermal stability, demulsibility, and nonferrous compatibility. The use of such ingredients results in quench oils that provide uniform steel hardness, long batch life, resistance to sludge formation, and minimum deformation. Thermrex D-10, R-21, and V-32 are mineral-oil blends carefully selected to approximate 100 SUS at 100°F. They yield consistent Relative Cooling Indices (RCI) of 95 to 160. Thermrex F-43 is a fast quench oil augmenting selected base stocks with additive technology to provide an RCI of 195. In addition, Thermrex R-21, V-32, F-43 are "gapped" to yield controlled distillation ranges from specific base stocks. The Thermrex Series oils are excellent media for rapidly cooling alloy steels to achieve optimum strength and toughness. The selection of the particular grade of quench oil depends on the cooling rate desired to prevent cracking and distortion. Thermrex Series oils D-10, R-21, V-32, and F-43 are most effective with agitation at batch temperatures of less than 150°F.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ExxonMobil-Thermrex-Series-V-32.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.8618 g/cc	0.8618 g/cc	
Kinematic Viscosity at 40°C (104°F)	16 cSt	16 cSt	

Thermal Properties	Metric	English	Comments
Pour Point	-3.00 °C	26.6 °F	
Flash Point	176 °C	349 °F	ASTM D92

Descriptive Properties	Value	Comments
Cooling Rate, ASTM D6200, F/Sec	116	
GM Quenchometer, %Quench Time, sec	19	ASTM D3520
GM Quenchometer, Relative Cooling Index	148/162	ASTM D3520

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China