

Fainplast Compounds Ethylplus 619 LD Polyethylene Cable Compound

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Wire/Cable Grade

Material Notes:

Polyethelene, halogen-free cable compound with superior thermo-mechanical properties, outstanding heat resistance, and high electrical properties
Black LDPE Sheathing
Information provided by Fainplast Compounds

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-Ethylplus-619-LD-Polyethylene-Cable-Compound.php

Physical Properties	Metric	English	Comments
Density	0.933 g/cc	0.0337 lb/in ³	ISO 1183
Melt Flow	0.35 g/10 min @Load 2.16 kg, Temperature 190 °C	0.35 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	46	46	ISO 868
Tensile Strength at Break	>= 15.0 MPa	>= 2180 psi	50 mm/min; ISO 527
Elongation at Break	>= 300 %	>= 300 %	50 mm/min; ISO 527

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 5.00e+15 ohm-cm	>= 5.00e+15 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 240 °C	356 - 464 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China