

Fainplast Compounds KL 96 Flexible PVC, Insulation for High Temperatures Lead Free

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Operating temperature 105°C

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-KL-96-Flexible-PVC-Insulation-for-High-Temperatures-Lead-Free.php

Physical Properties	Metric	English	Comments
Density	1.34 - 1.38 g/cc	0.0484 - 0.0499 lb/in³	ISO R 1184

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	94 - 98	94 - 98	ISO R 868
Tensile Strength at Break	>= 19.0 MPa	>= 2760 psi	ISO R 527
Elongation at Break	>= 260 %	>= 260 %	ISO R 527

Thermal Properties	Metric	English	Comments
Oxygen Index	27 %	27 %	ISO 4589

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm @Temperature 23.0 °C	1.00e+15 ohm-cm @Temperature 73.4 °F	ASTM D257

Descriptive Properties	Value	Comments
Thermal Stability (minutes)	200	CEI 20-34/3-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China