

Fainplast Compounds PMP 338 Flexible PVC, Extrusion Modified with PU

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

Material Notes:

Sheath PVC/PU for low temperatures

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fainplast-Compounds-PMP-338-Flexible-PVC-Extrusion-Modified-with-PU.php

Physical Properties	Metric	English	Comments
Density	1.19 - 1.23 g/cc	0.0430 - 0.0444 lb/in ³	ISO R 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73 - 77	73 - 77	ISO R 868
Tensile Strength at Break	15.0 MPa	2180 psi	ISO R 527
Elongation at Break	310 %	310 %	ISO R 527
Abrasion	90	90	[mm ³]; DIN 53516

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-36.0 °C	-32.8 °F	Cold Flex; ISO 458/2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China