

Fiberfil® J-60/20/E8 Polypropylene Homopolymer, 20% Glass Reinforced, Chemically coupled

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fiberfil-J-6020E8-Polypropylene-Homopolymer-20-Glass-Reinforced-Chemically-coupled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Water Absorption	0.030 %	0.030 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
	0.0040 cm/cm	0.0040 in/in	ASTM D955
	@Thickness 6.35 mm	@Thickness 0.250 in	
Melt Flow	9.0 g/10 min	9.0 g/10 min	230/2.16 (typical); ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100 - 110	100 - 110	ASTM D785
Tensile Strength, Yield	68.9 MPa	10000 psi	ASTM D638
Elongation at Yield	3.5 %	3.5 %	ASTM D638
Tensile Modulus	4.14 GPa	600 ksi	ASTM D638
Flexural Strength	93.1 MPa	13500 psi	ASTM D790
Flexural Modulus	3.79 GPa	550 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.641 J/cm	1.20 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	157 Â°C	315 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	149 Â°C	300 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China