

Fiberfil® PP-60/TC/20/VO/ND Polypropylene Homopolymer, 20% Talc Filled, Flame Retardant

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fiberfil-PP-60TC20VOND-Polypropylene-Homopolymer-20-Talc-Filled-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
Water Absorption	0.030 %	0.030 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
	0.012 cm/cm	0.012 in/in	ASTM D955
	@Thickness 6.35 mm	@Thickness 0.250 in	
Melt Flow	16 g/10 min	16 g/10 min	230/2.16 (typical); ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90 - 95	90 - 95	ASTM D785
Tensile Strength, Yield	24.8 MPa	3600 psi	ASTM D638
Elongation at Yield	10 %	10 %	ASTM D638
Tensile Modulus	3.79 GPa	550 ksi	ASTM D638
Flexural Strength	44.1 MPa	6400 psi	ASTM D790
Flexural Modulus	3.59 GPa	520 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.133 J/cm	0.250 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	132 Â°C	270 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	93.3 Â°C	200 Â°F	ASTM D648
Flammability, UL94	V-0	V-0	

Thermal Properties	@Thickness 1.50 mm Metric	@Thickness 0.0591 in English	Comments
--------------------	------------------------------	---------------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China