

Fiberfil® PP-60/TC/40/OP WT2595 Polypropylene Homopolymer, 40% Talc Filled, high opacity

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Information provided by FIBERFIL Engineered Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fiberfil-PP-60TC40OP-WT2595-Polypropylene-Homopolymer-40-Talc-Filled-high-opacity.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792
Water Absorption	0.030 %	0.030 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0050 - 0.0060 cm/cm	0.0050 - 0.0060 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
	0.0060 - 0.0070 cm/cm	0.0060 - 0.0070 in/in	ASTM D955
	@Thickness 6.35 mm	@Thickness 0.250 in	
Melt Flow	6.0 g/10 min	6.0 g/10 min	230/2.16 (typical); ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90 - 100	90 - 100	ASTM D785
Tensile Strength, Yield	29.6 MPa	4300 psi	ASTM D638
Elongation at Yield	15 %	15 %	ASTM D638
Tensile Modulus	5.17 GPa	750 ksi	ASTM D638
Flexural Strength	60.7 MPa	8800 psi	ASTM D790
Flexural Modulus	4.21 GPa	610 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.267 J/cm	0.500 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	143 Â°C	290 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	104 Â°C	220 Â°F	ASTM D648

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	204 - 227 Â°C	400 - 440 Â°F	
Front Barrel Temperature	182 - 199 Â°C	360 - 390 Â°F	
Nozzle Temperature	182 - 193 Â°C	360 - 380 Â°F	
Melt Temperature	199 - 232 Â°C	390 - 450 Â°F	
Mold Temperature	32.2 - 71.1 Â°C	90.0 - 160 Â°F	
Drying Temperature	76.7 Â°C	170 Â°F	Drying not normally required
Dry Time	2 hour	2 hour	Drying not normally required
Moisture Content	<= 0.20 %	<= 0.20 %	recommended for molding
Back Pressure	0.000 - 0.689 MPa	0.000 - 100 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China