

GRECO ISOPAK 569 ABS Resin

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Extruded

Material Notes:

Extrusion Grade Information provided by Greater Eastern Resins Industrial Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_GRECO-ISOPAK-569-ABS-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.03 g/cc	1.03 g/cc	ASTM D792
Water Absorption	0.30 % @Temperature 23.0 Â°C, Time 86400 sec	0.30 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955
Melt Flow	0.50 - 1.5 g/10 min @Load 5.00 kg, Temperature 200 Â°C	0.50 - 1.5 g/10 min @Load 11.0 lb, Temperature 392 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength	44.1 MPa	6400 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D412
Flexural Yield Strength	68.6 MPa	9960 psi	ASTM D790
Flexural Modulus	2.26 GPa	327 ksi	ASTM D790
Izod Impact, Notched	3.33 J/cm	6.25 ft-lb/in	ASTM D256 A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	88.0 Â°C	190 Â°F	ASTM D648
UL RTI, Mechanical without Impact	60.0 Â°C	140 Â°F	UL-746B
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Hot Wire Ignition, HWI	15 sec	15 sec	.062" and above; UL-746A

High Amp Arc Ignition, HAI Electrical Properties	200 arcs Metric	200 arcs English	.062" and above; UL-746A Comments
High Voltage Arc-Tracking Rate, HVTR	0.000 mm/min	0.000 in/min	.062" and above; UL-746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China