

Garlock 681 Vegetable Fiber Gasketing

Category: Polymer, Thermoplastic, Cellulosic

Material Notes:

Vegetable fiber with glue-glycerin binder (branded). Style 681 is designed for use in lightweight flanges and is compatible with water and most hydrocarbons. Information provided by Garlock Rubber Technologies

Order this product through the following link:

http://www.lookpolymers.com/polymer_Garlock-681-Vegetable-Fiber-Gasketing.php

Mechanical Properties	Metric	English	Comments
Tensile Strength	13.8 MPa	2000 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	
	@Pressure 1.38 MPa	@Pressure 200 psi	

Electrical Properties	Metric	English	Comments
Dielectric Strength	0.827 kV/mm	21.0 kV/in	Unconditioned; ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China