

Garlock Bay State 22 Natural/SBR Sheet Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

Material Notes:

Blend of natural and SBR rubber, specially compounded to be quick-sealing, non-hardening and heat resistant. Red, smooth rotocured finish. It conforms easily to uneven flange surfaces. Information provided by Garlock Rubber Technologies

Order this product through the following link:

http://www.lookpolymers.com/polymer_Garlock-Bay-State-22-NaturalSBR-Sheet-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70 - 85	70 - 85	
Tensile Strength	>= 4.83 MPa	>= 700 psi	
	6.89 MPa	1000 psi	Typical
Elongation at Break	>= 200 %	>= 200 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.2 Â°C	180 Â°F	
Minimum Service Temperature, Air	-28.9 Â°C	-20.0 Â°F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	11.0 kV/mm	280 kV/in	Unconditioned; ASTM D149
	@Thickness 3.17 mm	@Thickness 0.125 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China