

## Garlock GRAPH-LOCK® 3124/3126 Graphite Sheet Gasketing, Steel Wire Insert

Category: Carbon, Graphite

## **Material Notes:**

A laminated graphite sheet with a 316SS wire mesh insert. Pure exfoliated graphite flake material excels in extreme conditions, withstanding heat, pressure, and aggressive chemicals Proven fire-safe Seals easily under moderate bolt load, offers superior torque retention Retains dimensional stability in high temperatures; seals tightly even during pressure fluctuations Information provided by Garlock Rubber Technologies

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Garlock-GRAPH-LOCK-31243126-Graphite-Sheet-Gasketing-Steel-Wire-Insert.php

Physical Properties	Metric	English	Comments
Permeability	0.10	0.10	Gas Permeability, cc/min; DIN 3535 Part 4

Mechanical Properties	Metric	English	Comments
Tensile Strength	22.8 MPa	3300 psi	ASTM F152

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	649 °C	1200 °F	Steam
	454 °C	850 °F	
	@Pressure 13.8 MPa	@Pressure 2000 psi	
Minimum Service Temperature, Air	-240 °C	-400 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	98 %	98 %	Industrial Grade
	99.5 %	99.5 %	Nuclear Grade

Descriptive Properties	Value	Comments
Compressibility, %	40	ASTM F36
Creep Relaxation, %	17	ASTM F38
Sealability ASTM F37B, ml/hr	0.2	Nitrogen
	1.5	ASTM Fuel A

## **Contact Songhan Plastic Technology Co.,Ltd.**



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China