

Gichem GILAC D160/MT Acrylonitrile Butadiene Styrene (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Extruded

Material Notes:

ABS with good resilience, good thermal properties. Medium-High Injection speed. Information provided by GICHEM Gruppo Industriale Chimico

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gichem-GILAC-D160MT-Acrylonitrile-Butadiene-Styrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	ASTM D792
Water Absorption	0.30 %	0.30 %	ASTM D570
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
Melt Flow	8.0 g/10 min	8.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	42.0 MPa	6090 psi	ASTM D638
Elongation at Yield	25 %	25 %	ASTM D638
Flexural Modulus	2.30 GPa	334 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	ASTM D256
	1.00 J/cm	1.87 ft-lb/in	ASTM D256
	@Temperature 0.000 °C	@Temperature 32.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	102 °C	216 °F	ASTM D648
Vicat Softening Point	102 °C	216 °F	ASTM D1525/A
Flammability, UL94	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Flammability Test	75	75	[°C] Bilia; IEC 331
Oxygen Index	19 %	19 %	ASTM D2863
Glow Wire Test	650 °C	1200 °F	IEC 695-2-1

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric	English	Comments
Mold Temperature	50.0 - 60.0 °C	122 - 140 °F	
Drying Temperature	80.0 °C	176 °F	2 hours

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China