

Global 110 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Good flow Information provided by Global Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Global-110-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	23/23Â°C; ASTM D792
Linear Mold Shrinkage, Flow	0.0060 cm/cm	0.0060 in/in	ASTM D955
Melt Flow	18 g/10 min @Load 6.60 kg, Temperature 170 Â°C	18 g/10 min @Load 14.6 lb, Temperature 338 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	102 MPa	14800 psi	ASTM D638
Flexural Modulus	3.10 GPa	450 ksi	ASTM D790
Izod Impact, Notched	0.320 J/cm	0.600 ft-lb/in	ASTM D256

Descriptive Properties	Value	Comments
Forms	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China