

Global CPP-140 40% CaCO₃ Filled, Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Calcium Carbonate (CaCO₃) Filler

Material Notes:

Information provided by Global Polymers Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer_Global-CPP-140-40-CaCO₃-Filled-Polypropylene.php](http://www.lookpolymers.com/polymer_Global-CPP-140-40-CaCO3-Filled-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 °C	10 g/10 min @Load 4.76 lb, Temperature 446 °F	L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	23.4 MPa	3400 psi	ASTM D638
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	0.427 J/cm	0.800 ft-lb/in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China