

Global GPEI-230 30% Glass Filled Reinforced Polyetherimide Alloy

Category : Polymer , Thermoplastic , Polyetherimide (PEI) , Polyetherimide (PEI), 30% Glass Fiber

Material Notes:

Information provided by Global Polymers Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Global-GPEI-230-30-Glass-Filled-Reinforced-Polyetherimide-Alloy.php

Physical Properties	Metric	English	Comments
Density	1.51 g/cc	0.0546 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ASTM D955
Melt Flow	4.0 g/10 min @Load 6.60 kg, Temperature 345 Â°C	4.0 g/10 min @Load 14.6 lb, Temperature 653 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	165 MPa	24000 psi	ASTM D638
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China