

Goodfellow Nickel/Iron/Molybdenum Alloy

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

Information provided by Goodfellow.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Goodfellow-NickelIronMolybdenum-Alloy.php

Component Elements Properties	Metric	English	Comments
Iron, Fe	15.5 %	15.5 %	
Molybdenum, Mo	4.5 %	4.5 %	
Nickel, Ni	80 %	80 %	

Electrical Properties	Metric	English	Comments
Magnetic Permeability	50000	50000	Initial
	250000	250000	Maximum
Magnetic Coercive Force, Hc	0.0151 Oe	0.0151 Oe	
Magnetic Remanence, Br	3500 Gauss	3500 Gauss	
Curie Temperature	450 °C	842 °F	

Descriptive Properties	Value	Comments
Saturation Induction (T)	0.8	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China