

Goodfellow Platinum 92/Tungsten 8 Alloy

Category : Metal , Nonferrous Metal , Precious Metal , Platinum Alloy

Material Notes:

Information provided by Goodfellow.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Goodfellow-Platinum-92Tungsten-8-Alloy.php

Physical Properties	Metric	English	Comments
Density	21.3 g/cc	0.770 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	895 - 2070 MPa	130000 - 300000 psi	

Thermal Properties	Metric	English	Comments
Melting Point	1870 - 1910 °C	3400 - 3470 °F	
Solidus	1870 °C	3400 °F	
Liquidus	1910 °C	3470 °F	

Component Elements Properties	Metric	English	Comments
Platinum, Pt	92 %	92 %	
Tungsten, W	8.0 %	8.0 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China