

Gouda Vuurvast FI 25-15 Insulating Refractory Brick

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

This data represents average values, obtained from samples that were cut from standard bricks. Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-FI-25-15-Insulating-Refractory-Brick.php

Physical Properties	Metric	English	Comments
Density	1.45 - 1.55 g/cc	0.0524 - 0.0560 lb/in ³	Apparent

Mechanical Properties	Metric	English	Comments
Compressive Strength	12.0 - 18.0 MPa	1740 - 2610 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.480 - 0.680 W/m-K	3.33 - 4.72 BTU-in/hr-ft ² -°F	
	@Temperature 200 °C	@Temperature 392 °F	
	0.530 - 0.730 W/m-K	3.68 - 5.07 BTU-in/hr-ft ² -°F	
	@Temperature 600 °C	@Temperature 1110 °F	
	0.600 - 0.800 W/m-K	4.16 - 5.55 BTU-in/hr-ft ² -°F	
	@Temperature 1000 °C	@Temperature 1830 °F	
Maximum Service Temperature, Air	1250 °C	2280 °F	
Shrinkage	0.200 - 0.600 %	0.200 - 0.600 %	
	@Temperature 1230 °C, Time 86400 sec	@Temperature 2250 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	37 %	37 %	
Fe ₂ O ₃	2.0 %	2.0 %	
SiO ₂	56 %	56 %	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Segercone Descriptive Properties	31 Value	Comments
--	----------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China