

Gouda Vuurvast VIBRON 165 Dense Vibrating Refractory Castable

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

Description: Vibron 165 is a low cement castable based on andalusite and especially fit for the production of prefab elements. Remarks:

Indicated values apply to vibrated products. Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-VIBRON-165-Dense-Vibrating-Refractory-Castable.php

Physical Properties	Metric	English	Comments
Bulk Density	2.65 - 2.75 g/cc	0.0957 - 0.0994 lb/in ³	After drying at 110 ^o C
Particle Size	<= 6000 μ m	<= 6000 μ m	Grain Size

Mechanical Properties	Metric	English	Comments
Compressive Strength	45.0 - 55.0 MPa	6530 - 7980 psi	Cold Crushing Strength
	@Temperature 100 ^o C	@Temperature 212 ^o F	
	100 - 120 MPa	14500 - 17400 psi	Cold Crushing Strength
	@Temperature 1400 ^o C	@Temperature 2550 ^o F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.20 - 1.30 W/m-K	8.33 - 9.02 BTU-in/hr-ft ² - ^o F	
	@Temperature 100 ^o C	@Temperature 212 ^o F	
	1.23 - 1.33 W/m-K	8.54 - 9.23 BTU-in/hr-ft ² - ^o F	
	@Temperature 600 ^o C	@Temperature 1110 ^o F	
	1.45 - 1.65 W/m-K	10.1 - 11.5 BTU-in/hr-ft ² - ^o F	
	@Temperature 1400 ^o C	@Temperature 2550 ^o F	
Maximum Service Temperature, Air	1600 ^o C	2910 ^o F	
Shrinkage	-0.500 - 0.500 %	-0.500 - 0.500 %	Permanent Linear Change
	@Temperature 1400 ^o C	@Temperature 2550 ^o F	

Component Elements Properties	Metric	English	Comments
-------------------------------	--------	---------	----------

AI2O3 Component Elements Properties	63 % Metric	63 % English	Comments
Fe2O3	<= 1.0 %	<= 1.0 %	
SiO2	32 %	32 %	

Descriptive Properties	Value	Comments
Material Consumption per 1 m3	2650 kg	
Mixing Water	3.5-4 liters	per 100 kgs dry material

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China