

Gromax CCP PBT 1100-220S

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Unreinforced, Molded

Material Notes:

Product Description: PBT unreinforced and impact-modified injection molding grade. Characteristics:Low warp age, high toughness and excellent dimensional stabilityExcellent glossy surface and less-gas decompositionExcellent electrical property Excellent mechanic and chemical property Excellent weatherabilityExcellent wear property Excellent moldability High resistance to fuels, oil, fats and many solvents.Information provided by Gromax Enterprises Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gromax-CCP-PBT-1100-220S.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792
Moisture Absorption	0.0600 % @Time 86400 sec	0.0600 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage	0.0090 - 0.018 cm/cm @Thickness 1.60 mm	0.0090 - 0.018 in/in @Thickness 0.0630 in	horizontal; ASTM D955
	0.012 - 0.021 cm/cm @Thickness 1.60 mm	0.012 - 0.021 in/in @Thickness 0.0630 in	vertical; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	117	117	ASTM D785
Tensile Strength	39.2 MPa	5690 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Strength	55.0 MPa	7980 psi	ASTM D790
Flexural Modulus	1.57 GPa	228 ksi	ASTM D790
Izod Impact, Notched	>= 4.41 J/cm @Thickness 6.35 mm	>= 8.27 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 Âµm/m-Â°C	50.0 Âµin/in-Â°F	ASTM D696
Melting Point	225 Â°C	437 Â°F	DSC
Deflection Temperature at 0.46 MPa (66 psi)	140 Â°C	284 Â°F	ASTM D648

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ASTM D257
Dielectric Constant	3.3	3.3	ASTM D150
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Dissipation Factor	0.0010	0.0010	ASTM D150
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
Arc Resistance	90 sec	90 sec	ASTM D495

Processing Properties	Metric	English	Comments
Processing Temperature	230 - 260 Â°C	446 - 500 Â°F	
Nozzle Temperature	245 - 250 Â°C	473 - 482 Â°F	
Mold Temperature	30.0 - 100 Â°C	86.0 - 212 Â°F	suitable temperature 40-60Â°C
Injection Pressure	50.0 - 100 MPa	7250 - 14500 psi	
Hold Pressure	30.0 - 70.0 MPa	4350 - 10200 psi	
Back Pressure	0.000 - 0.300 MPa	0.000 - 43.5 psi	
Screw Speed	60 - 120 rpm	60 - 120 rpm	to be chosen in such a way that plasticizing time is just within cooling time

Descriptive Properties	Value	Comments
Injection Rate	middle-fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China